

R1

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2001-180962

(43)Date of publication of application : 03.07.2001

(51)Int.Cl.

C03C 3/06

C03B 8/04

C03B 20/00

(21)Application number : 11-366308

(71)Applicant : ASAHI GLASS CO LTD

(22)Date of filing : 24.12.1999

(72)Inventor : IKUTA YORISUKE
KIKUKAWA SHINYA
SHIMODAIRA KENSHO
MASUI AKIO

(54) SYNTHESIZED QUARTZ GLASS AND MANUFACTURING METHOD

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a synthesized quartz glass without decrease of transmission factor by an ultraviolet irradiation of wavelength 150-200 nm and the manufacturing method.

SOLUTION: A synthesized quartz glass is characterized by an OH group concentration of 100 ppm or less, hydrogen molecule concentration less than 1×10^{17} molecule/cm³, and no reduction type of defect substantially, therein; and by that change of absorbance index in 150-200 nm after irradiation of an ultraviolet ray of wavelength 172 nm at an illuminance of 10 mW/cm² for 15 kJ/cm² is 0.2 cm⁻¹ or less.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]